



Red Alicante – Technical Data Sheet

Stone Type: Natural Marble

Origin: Spain (mainly from the region of Alicante)

Finishes Available

Polished (most common)

Honed

Brushed

Tumbled

Recommended Uses

Interior flooring

Wall cladding

Bathroom vanities

Staircases

Decorative Accents

Fireplace surrounds

www.naturalstonespain.com



Red Alicante

Physical & Mechanical Properties

Color: Deep reddish background with irregular White veining

Petrography: Fossiliferous limestone (calcareous marble)

Water Absorption (by weight): ~0.27%

Apparent Density: ~2,690 kg/m³

Open Porosity: ~0.7%

Compressive Strength: ~110 MPa

Flexural Strength: ~13 MPa

Abrasion Resistance: ~2.4 mm

Mohs Hardness: 3-4

Thermal Expansion Coefficient: ~6.3 × 10⁻⁶ /°C

Frost Resistance: Low (not suitable for freeze-thaw environments)

www.naturalstonespain.com